


**AMENDMENTS TO THE CLAIMS (AS ON AMENDED SHEETS ANNEXED TO IPER)**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (original) A radiation-curable liquid resin composition comprising:

(A) 20-90 wt% of a urethane (meth)acrylate oligomer, and

(B) 1-35 wt% of a monomer shown by the following formula (1),



wherein R<sup>1</sup> represents a hydrogen atom or a methyl group, R<sup>2</sup> and R<sup>3</sup> individually represent a hydrogen atom or an alkyl group having 1-4 carbon atoms, R<sup>4</sup> represents a hydrogen atom or a methyl group, and n represents an integer of 1-6.

2. (original) The radiation-curable liquid resin composition according to claim 1 comprising 65-90 wt% of a urethane (meth)acrylate oligomer.

3. (currently amended) The radiation-curable liquid resin composition according to claim 1 ~~or 2~~, wherein the urethane (meth)acrylate oligomer is obtained by reacting a polyol compound (a), a polyisocyanate (b), and a hydroxy-functional ethylenically unsaturated monomer (c).

4. (currently amended) The radiation-curable liquid resin composition according to claim 1 ~~or 2~~, wherein 10-80 wt% of the urethane (meth)acrylate oligomer is obtained by reacting a polyisocyanate compound (b) and a hydroxy-functional ethylenically unsaturated monomer (c).

5. (original) The radiation-curable liquid resin composition according to claim 4, wherein 10-50 wt% of the urethane (meth)acrylate oligomer is obtained by reacting a polyisocyanate compound (b) and a hydroxy-functional ethylenically unsaturated monomer (c).

6. (currently amended) The radiation-curable liquid resin composition according to claim 4 ~~or 5~~, the composition further comprising a urethane (meth)acrylate oligomer obtained by reacting a polyol compound (a), a polyisocyanate (b), and a hydroxy-functional ethylenically unsaturated monomer (c).

7. (currently amended) The radiation-curable liquid resin composition according to ~~any one of claims 3-6~~ claim 3, wherein the oligomer obtained by reacting a polyisocyanate compound (b) and a hydroxy-functional ethylenically unsaturated monomer (c) is an oligomer obtained by reacting 2-hydroxyethyl (meth)acrylate and 2,4-tolylene diisocyanate.

8. (currently amended) The radiation-curable liquid resin composition according to ~~any one of claims 1-7~~ claim 1, wherein the monomer (B) is chosen from the group consisting of 2-(2'-vinylloxyethoxy)ethyl (meth)acrylate and 2-vinylloxyethyl (meth)acrylate.

9. (currently amended) The radiation-curable liquid resin composition according to ~~any one of claims 1-8~~ claim 1, further comprising a reactive diluent (C), wherein (C) is not covered by the definition of component (B).

10. (original) The radiation-curable liquid resin composition according to claim 9 comprising 1-33 wt% of reactive diluent (C).

11. (currently amended) The radiation-curable liquid resin composition according to ~~any one of claims 1-10~~ claim 1, wherein the composition has a viscosity of 1.0-6.0 Pa·s at 25°C.

12. (currently amended) Use of the radiation-curable liquid resin composition according to ~~any one of claims 1-11~~ claim 1 as a primary coating, secondary coating, ink composition or matrix material on an optical glass fiber.

13. (currently amended) A coated optical fiber comprising a glass optical fiber having a primary coating, a coated optical fiber comprising a glass optical fiber having a primary coating and a secondary coating, a coated optical fiber comprising a glass optical fiber having a primary coating, a secondary coating and an upjacketing coating,

a coated optical fiber comprising a glass optical fiber and a single coating, a coated optical fiber comprising a glass optical fiber, a single coating and an upjacketing coating, and each coated fiber optionally having an ink composition applied thereon, and to an optical fiber ribbon comprising at least two of said coated and optionally inked optical fibers wherein at least one of said coating or composition is derived from a radiation-curable composition as described in ~~any one of claims 1-11~~ claim 1.

14. (currently amended) Coated and optionally inked optical fiber comprising a glass optical fiber having a primary coating, a secondary coating, and optionally an ink composition applied thereon, wherein at least one of said coatings or ink compositions is derived from a radiation-curable composition according to ~~any one of claims 1-11~~ claim 1.

15. (currently amended) An optical fiber ribbon comprising a plurality of coated and optionally inked optical fibers according to claim 13 ~~or claim 14~~ held together by a matrix material.

16. (currently amended) An optical fiber ribbon comprising a plurality of coated and optionally inked optical fibers held together by a matrix material, wherein the matrix material is derived from a radiation-curable resin composition according to ~~any one of claims 1-11~~ claim 1.